



M/s. Chhaganlal Dharamchand Shah

SAILMA HIGH STRENGTH MICRO ALLOY STRUCTURE STEEL (semi killed)

CHEMICAL COMPOSITION					
GRADE	C% (MAX)	Mn% (MAX)	S% (MAX)	P% (MAX)	Nb + V + Ti % (MAX)
SALIMA 300	0.25	1.5	0.055	0.055	0.2
SALIMA 300HI	0.2	1.5	0.04	0.04	0.2
SALIMA 350	0.25	1.5	0.04	0.04	0.2
SALIMA 350HI	0.2	1.5	0.04	0.04	0.2
SALIMA 410	0.25	1.5	0.04	0.04	0.2
SALIMA 410HI	0.2	1.5	0.04	0.04	0.2
SALIMA 450	0.25	1.5	0.04	0.04	0.2
SALIMA 450HI	0.2	1.5	0.04	0.04	0.2

Since 1969