



M/s. Chhaganlal Dharamchand Shah

SALIMA HIGH STRENGTH MICRO ALLOY STRUCTURE STEEL (semi killed)

MECHANICAL PROPERTIES

GRADE	UTS (Mpa)	YS (Mpa) Mn	Ei % Min 5.65 √80	IMPACTY CHARPY		BEND TEST
				0°C-20°C Joules (Min)		
SALIMA 300	440-560	300	20			3T
SALIMA 300HI	440-560	300	21	40		3T
SALIMA 350	490-610	350	20	-		3T
SALIMA 350HI	490-610	350	21	40	30	3T
SALIMA 410	510-660	410	19	-		3T
SALIMA 410HI	540-660	410	20	35	25	3T
SALIMA 450	570-720	450	18	-		3T
SALIMA 450HI	570-720	450	19	30	20	3T

Since 1969